

Urethane Concrete Cove Base

Description:

Terroxy Urethane Concrete Cove Base (**UC Cove Base**) is a three-component (with additional pigment pack when required) water-based polyurethane concrete system for flooring applications. This system is odorless, and contains no VOC's or HAP's. Properties include excellent chemical resistance against acids, bases, oils, and organic solvents. This product is placed and finished with a radius trowel for a smooth, sealed finish. This product develops a hard, scratch resistant surface and withstands exposure to thermal shock and moisture vapor transmission. Before application, thoroughly prepare surface by grinding or shot-blasting. UC Cove Base is available in a variety of colors. Pigment options include color packs or pre-pigmented resin.

Product Benefits:

- Up to 99% RH concrete moisture tolerance
- Excellent chemical and stain resistance
- Impact and abrasion resistant
- Rapid cure & hardness development
- Excellent bond strength
- Durable and easy to clean
- Water Based, Zero VOC Formulation
- Low temperature cure
- Thermal shock and cycling resistant
- High heat resistance
- Seamless transition to floor

Typical Applications:

- Kitchens & Cafeterias
- Industrial uses especially with heavy traffic
- Processing plants
- Locker rooms and rest rooms
- Clean rooms & laboratories
- Cold storage areas
- Cook/chill areas
- Aerospace
- Areas requiring high performance

Coverage:

Typical coverage for a kit of UC Cove Base is between 14 ft-18.5 ft based on a 4"-6" yield at 1/4" thickness.

Concrete Substrate Preparation:

Terroxy UC Cove Base can be applied to a variety of substrates given that the surface is properly prepared. Preparation of surfaces other than concrete will depend on the type of substrate.

1. Concrete slab shall have an efficient moisture/vapor barrier (suggested minimum: 15 mils / 0.4mm thickness) directly under the concrete slab.
2. Allow substrate to cure a minimum of 7 days.
3. Sub-floor should be level - maximum variation not to exceed 1/4" in 10 ft (6.35 mm in 3m).
4. The recommended preparation method is shot blasting to a CSP 3-5.
5. Surface to receive Terroxy Urethane Concrete should have a steel trowel finish.
6. Substrate should not been treated with a curing agent as this may prevent bonding. If curing agent present, surface must be shot blasted.

** For specific preparation guidelines, contact your T&M representative.

Installation Instructions

Mixing:

Terroxy UC Cove Base is a three-component product (with additional color pack when required) and must be properly mixed and applied in order to perform as specified.

Add 4 oz. of Urethane Concrete Colorant to UC Cove Base Part A and blend gently until color is uniform. Be sure to scrape all contents of the colorant into the Part A. Add UC Cove Base Part B to pigmented UC Cove Base Part A and mix with medium agitation for approximately 20 seconds. Pour mixture into a 5-gallon pail and add UC Cove Base Part C powder and mix until uniform. Material has 10-15 minute working time at 72°F.

Mix ratio: 1 quart Part A (with 4 oz. pigment pack), 1 quart Part B, 20 lbs. Part C (neutral)

Note: Do not split kits or mix off ratio

Application:

Apply UC Cove Base in a temperature controlled environment (ideal temperature range is 60-80°) at a spread rate of 1/4" thickness. Smooth and finish with a radius trowel. This material will cure faster in hot or humid conditions. Very cold temperatures will cause system to be slightly thicker and may make installation more difficult. Care should be taken to apply and level material quickly.

Coverage per kit of UC Cove Base (at 1/4" thickness):

4" yield - 18.5 ft.

6" yield - 14 ft.

Limitation:

Rapid cure. Do not mix more material than can be applied in 10 - 15 minutes. Slab on grade requires 15mil vapor/moisture poly-barrier. Moisture limits for moisture vapor transmission of Terroxy Urethane Concrete are 20lbs. /1000 sq. ft. /24 hours using the calcium chloride test per ASTM F-1869 or 99% relative humidity using in-situ RH testing per ASTM F-2170.

Do not thin this product. Solvents may prevent proper curing. Substrate temperatures should be 38°F (3.3°C) minimum and rising. For best results, material should be maintained and stored at temperatures between 50° - 80°F (10° - 27°C). Additionally, for installations between 38°-55°F, use of additional catalyst package is necessary for full cure. Please contact technical support for further information.

IMPORTANT: This product is sensitive to liquid epoxy materials. Contamination with liquid epoxy materials will also cause excessive heat and product failure.

Due to various raw materials used in Terroxy Urethane Concrete Systems, the finished color of these systems may appear different from samples seen on Terroxy Resinous color charts. The UC Cove Base color may be a shade different from the floor; if necessary, apply UC Topcoat (pigmented) to match the cove base with the floor. For physical color samples of finished Terroxy Urethane Concrete systems, contact your technical representative.

Cure Time:

Allow to cure approximately 6 hours at 72°F (22.2°C) surface temperature before opening to light traffic. Full cure

Property	Method	Results
Flexural Strength	ASTM-C 580	2,300 psi (15.9 MPa)
Abrasion Resistance	ASTM D-4060 C-S17 Wheel 1000 Cycles	20-30 mg loss
Flammability	ASTM D-635	Self-extinguishing over concrete
Hardness	ASTM D-2240, Shore D	80-85
Tensile Strength	ASTM C-307	1,000 psi minimum (6.9 MPa)
Compressive Strength	ASTM C-579	7,700 psi (53.1 MPa)
Adhesion	ACI 503R	350 psi (2.4 MPa) 100% Concrete Failure
Impact Resistance	MIL D-3134F 4.7.3	Withstands 16 ft/lbs without cracking, delaminating or chipping
Thermal Coefficient of Expansion	ASTM C-531	0.89 x 10 ⁻⁵ inches per inch/degrees Fahrenheit maximum (1.6 x 10 ⁻⁵ mm/°C)
Fungus & Bacterial Resistance	MIL F-52505 4.4.2.11	Will not support growth of fungus or bacteria
Water Absorption	ASTM C-413	0.10%
Chemical Resistance	ASTM D-1308	No deleterious effects when exposed to: Alcohol Ethylene Glycol Fats, Oils & Sugars Gasoline, Diesel & Kerosine Hydrochloric Acid (<35%) Lactic Acid (Milk) Mineral Oils Most Organic Solvents Muriatic Acid Nitric Acid (<10%) Nitric Acid (<30%) Slight Softening PM Acetate Phosphoric Acid (<50%) Potassium Hydroxide (<50%) Sodium Hydroxide (<50%) Sulfuric Acid (<50%) Slight Gloss Loss Water Xylene

Clean Up

Clean up mixing and application equipment immediately after use. Use acetone or denatured alcohol. Observe all fire and health precautions when handling or storing solvents

Maintenance:

After completing the application of UC Cove Base, the installer should provide the owner with proper maintenance instructions. If the floors become slippery due to animal fats, oil, grease, soap or other topical residue, promptly remove contaminants and rinse thoroughly.

Terroxy Urethane Concrete is easily cleaned with neutral pH Balance Cleaners or detergents. Routine hand scrubbing is recommended for all surfaces having a slip resistant texture.

Technical Service:

Terrazzo & Marble Supply Companies, distributor of Terroxy Resin Systems, provides services and consultations on material selection, specifications and troubleshooting concerning proper installation. Contact our **Terrazzo Sales Desk at 800.7.MARBLE** or **T&M Technical Department at 708.385.6633** for questions or assistance.

Precautions:

Refer to cautionary information printed on the product container. For medical emergencies, contact Chemtrec, the Chemical Emergency Transportation Center, at 800.424.9300.

Warranty:

Terrazzo & Marble Supply Companies warrants for a period of one (1) year that Terroxy UC Cove Base will be free of manufacturing defects and will conform to published specification when handled, stored, mixed and applied in accordance to recommendations of Terrazzo & Marble. If Terroxy UC Cove Base fails to meet this warranty, the liability of Terrazzo & Marble will be limited to replacement of any non-conforming Terroxy UC Cove Base only if notice of such non-conformity is given to Terrazzo & Marble within one (1) year from the delivery of materials. Terrazzo & Marble may, according to its discretion, refund the price received by Terrazzo & Marble in lieu of replacing the Terroxy UC Cove Base. No customer, distributor or representative of Terrazzo & Marble is authorized to change or modify the published specification of this warranty in any way. No one is authorized to make oral warranties on behalf of Terrazzo & Marble. In order to obtain replacement or refund, the customer must provide written notice containing full details of the nonconformity. Terrazzo & Marble reserves the right to inspect the non-conforming Terroxy UC Cove Base prior to replacement. Except for the expressed warranty stated above, there is no other warranties, expressed or implied, including without limitation, implied warranty of merchantability or fitness for purpose. Terrazzo & Marble's obligation shall not extend beyond the obligations expressly undertaken above and Terrazzo & Marble shall have no liability or responsibility to the purchaser or any third party for any loss, cost, expense, damage or liability, whether direct or indirect, or for incidental or consequential damages.

Distributed By:



464 Northgate Parkway
Wheeling, IL 60090
p: 847.947.7300

12632 Monarch St. Unit B
Garden Grove, CA 92841
p: 714.901.1400

6100 Seaforth St.
Baltimore, MD 21224
p: 410.633.6200



5789 Steeles Avenue West
Toronto, ON M9L 2W3
p. 416.789.5387